

## PLAIN COPPER TUBING SPECS

# Wieland

**Wieland South Africa (Pty) Ltd**

56 Plantation Rd Eastleigh , Edenvale

PHONE : (011) 609-8325

FAX : (011) 452-3791

[www.wielandsa.com](http://www.wielandsa.com)

[info@wielandsa.com](mailto:info@wielandsa.com)

						PTC	
TUBE	O.D.	WALL Th.	Kg/m	Cond.	Length	Mpa	Bar
CU	4,76	0,52	0,062	H/H	3100	18.01	180.1
CU	6,35	0,71	0,112	H/H	6100	18.43	184
CU	9,53	1,27	0,294	H/H	6100	21.98	219.8
CU	12,7	1,22	0,392	H/H	6100	15.84	158.4
CU	15,7	1,25	0,506	Annealed	5800	10.74	107.4
CU	15,88	1,28	0,523	H/H	6100	13.29	132.9
CU	15,88	1,63	0,650	H/H	6100	16.93	169.3
CU	18,8	1,28	0,628	Annealed	5800	9.18	91.8
CU	19,05	1,28	0,637	H/H	6100	11.08	110.8
CU	19,05	1,63	0,795	H/H	6100	14.11	141.1

**FOR PRICING PLEASE CONTACT SALES : [LYNNE@WIELANDSA.COM](mailto:LYNNE@WIELANDSA.COM) / [CHRIS@WIELANDSA.COM](mailto:CHRIS@WIELANDSA.COM)**

\* ALL TUBE STANDARDS ACCORDING TO BS2871 - C106

\* ALL DIMENSIONS IN mm UNLESS OTHERWISE STATED